## **ASPHALT SURFACE AREAS AND RATES FOR TRAVEL LANES**

DESCRIPTION	RATE	BASIS	QUANTITIES	
SEAL COAT				
FIRST COURSE				
ASPH (AC-20-XP)	0.40 GAL / SY#	, SY	, GAL	
AGGR (TY-PB GR-3)	1 CY / 90 SY	, SY	CY	
SECOND COURSE				
ASPH (AC-20-XP)	0.28 GAL / SY#	, SY	, GAL	
AGGR (TY-PB GR-4 SAC-B)	1 CY / 120 SY	, SY	CY	

<sup>#</sup> RATE MAY BE VARIED BY ENGINEER OF RECORD DEPENDING ON FIELD CONDITIONS AND OTHER FACTORS IN ADVANCE OF MANDATORY PRE-SURFACING MEETING WITH APPROVAL OF THE CITY.

## NOTES:

- 1. ASPHALT SHALL ONLY BE PLACED JUNE 1 THROUGH AUGUST 31 UNLESS OTHERWISE APPROVED BY THE CITY.
- 2. PLACE FIRST COURSE SEAL COAT USING AC-20-XP ASPHALT ON PRIMED SURFACE (OR EXISTING ASPHALTIC SURFACE) AT A RATE OF 0.40 GAL / SY (UNDERSTANDING RATE MAY REQUIRE MODIFYING BASED ON FIELD CONDITIONS AND OTHER FACTORS)<sup>#</sup> AND IMMEDIATELY COVER WITH AGGR (TY-PB GR-3) AT RATE OF 1 CY / 90 SY, ROLL, CURE, AND SWEEP.
- 3. PLACE SECOND COURSE SEAL COAT ON FIRST COURSE SEAL COAT USING AC-20-XP ASPHALT AT A RATE 0.28 GAL / SY (UNDERSTANDING RATE MAY REQUIRE MODIFYING BASED ON FIELD CONDITIONS AND OTHER FACTORS)<sup>#</sup> AND IMMEDIATELY COVER WITH AGGR (TY-PB GR-4 SAC-B) AT RATE OF 1 CY / 120 SY, ROLL, CURE, AND SWEEP.
- 4. MATERIALS AND WORK SHALL BE IN ACCORDANCE WITH CURRENT TXDOT SPECIFICATIONS.

## **SEAL COAT SURFACING FOR DEVELOPER PROJECTS**

(USE REQUIRES MODIFICATION BY ENGINEER OF RECORD FOR BASIS & QUANTITIES AND APPROVAL BY THE CITY)



ENGINEEDING BIVIOLON		REVISIONS				
<b>ENGINEERING DIVISION</b>	NO.	COMMENTS	BY	DATE		
DISCLAIMER: THE USE OF THIS STANDARD IS GOVERNED BY THE "TEXAS						
ENGINEERING PRACTICE ACT". NO WARRANTY OF ANY KIND IS MADE BY						
THE CITY OF WACO FOR ANY PURPOSE WHATSOEVER. THE CITY OF WACO						
ASSUMES NO RESPONSIBILITY FOR THE CONVERSION OF THIS STANDARD						
TO OTHER FORMATS OR FOR INCORRECT RESULTS OR DAMAGES				·		
RESULTING FROM ITS USE.	##	DESCRIPTION	FL	MM/DD/YYYY		

DATE 11/15/2024