

PAVEMENT / SURFACE REPLACEMENT DETAILS

- (1) SEE <u>ST-30</u> AND APPLICABLE <u>ST-33</u> AND/OR <u>ST-34</u> FOR SAW CUT AND PAVEMENT REPLACEMENT DETAILS.
- (2) SEE ST-37 AND APPLICABLE ST-35 AND/OR ST-36 FOR SAW CUT AND PAVEMENT REPLACEMENT DETAILS.
- TYPE "A" MATERIAL PER STANDARD SPECIFICATIONS FOR CONSTRUCTION, SECTION 4.2 EXCAVATION AND BACKFILL, PART 2: PRODUCT, A. MATERIALS, 3. TRENCH BACKFILL, A. TYPE "A." MATERIAL MECHANICALLY COMPACTED TO 95% OF THE MAXIMUM DRY DENSITY (TEX-113-E) OR CONTROLLED LOW STRENGTH MATERIAL.
- USE CONTROLLED LOW STRENGTH MATERIAL TO BACKFILL ALL TRENCHES 18 IN. OR NARROWER, IN THE RIGHT-OF-WAY AND PUBLIC EASEMENTS.
- (5) EDGE TO BE STRAIGHT, SQUARE AND PARALLEL TO SIDES OF TRENCH.
- (6) 6 IN. MIN. TOPSOIL AND SEED OR SOD SUBSIDIARY.
- (7) TXDOT ITEM 247 FLEXIBLE BASE TYPE A GRADE 1-2 MINIMUM PLASTICITY INDEX 5.
- (8) SEE G-10 FOR BACKFILL MATERIAL REQUIREMENTS AND FOR INSTALLATION.

		REVISIONS			DATE	
100	ENGINEERING DIVISION	NO.	COMMENTS	BY	DATE	DATE 01/01/2024
	DISCLAIMER: THE USE OF THIS STANDARD IS GOVERNED BY THE "TEXAS ENGINEERING PRACTICE ACT". NO WARRANTY OF ANY KIND IS MADE BY					01/01/2024
CITYOF	THE CITY OF WACO FOR ANY PURPOSE WHATSOEVER. THE CITY OF WACO ASSUMES NO RESPONSIBILITY FOR THE CONVERSION OF THIS STANDARD					\sim
WACO	TO OTHER FORMATS OR FOR INCORRECT RESULTS OR DAMAGES					G-9
	RESULTING FROM ITS USE.	##	DESCRIPTION	FL	MM/DD/YYYY	