

## CONSTRUCTION MATERIAL SAMPLING AND TESTING MATRIX - 2 OF 2

Construction Operation	Standard Specifications		Standard Details	Applicable Testing	Minimum Frequency of Testing	
	Material Specs	Construction Specs				
Surface Course	Testing - Section 3.7					
Hot-Mix Asphaltic Concrete Pavement	Section 3.3, Part 2	Section 3.3, Part 3	<a href="#">ST-2</a>	Extraction, Gradation, Stability & Flow, Densities, Thickness	1 sample per day of paving operations. Densities - one per 600 LF of paving. Thickness - each street per 1,000 LF in each lane	
Portland Cement Concrete Pavement	Section 3.6, Part 2	Section 3.6, Part 3	<a href="#">G-7</a> , <a href="#">ST-1</a> , <a href="#">ST-4</a> , <a href="#">ST-6</a> <a href="#">ST-7</a> , <a href="#">ST-8</a> , <a href="#">ST-9</a>	Air Content (if specified) , Slump, Compressive Strength	1 set of 4 cylinders per 150 CY but no less than 2 sets per day	
Concrete	Testing - Section 5.6					
Curb and Gutter	Section 5.1, Part 2 & 3	Section 5.3, Part 3	<a href="#">G-7</a> <a href="#">ST-1</a> <a href="#">ST-7</a> <a href="#">ST-15</a> , <a href="#">ST-16</a> , <a href="#">ST-17</a> <a href="#">ST-18</a> , <a href="#">ST-19</a> , <a href="#">ST-20</a>	Slump Compressive Strength	One set of 4 cylinders per placement for the first 5 placements then one set for every other placement thereafter. (max. of 2 sets per day) *Different trucks on the same site at different times of the day constitute different placements.	
Drive Approach		Section 5.4, Part 3	<a href="#">G-7</a> , <a href="#">ST-1</a> , <a href="#">ST-23A</a> <a href="#">ST-23B</a> , <a href="#">ST-24A</a> , <a href="#">ST-24B</a> <a href="#">ST-25A</a> , <a href="#">ST-25B</a> , <a href="#">ST-26</a>			
Valley & Fillet			<a href="#">G-7</a> <a href="#">ST-1</a> <a href="#">ST-18</a> <a href="#">ST-19</a>			
Sidewalk, Curb Ramps, & Retaining Walls		Section 5.4, Part 3	<a href="#">G-7</a> , <a href="#">SW-1</a> , <a href="#">SW-2</a> , <a href="#">SW-3</a> , <a href="#">SW-4</a> , <a href="#">SW-5</a> , <a href="#">SW-6</a> , <a href="#">SW-7</a> , <a href="#">SW-8</a> , <a href="#">SW-9</a> , <a href="#">SW-10</a> , <a href="#">SW-11</a> , <a href="#">SW-12</a> , <a href="#">SW-13</a> , <a href="#">SW-14</a> , <a href="#">SW-15</a> , <a href="#">SW-16</a> , <a href="#">SW-17</a> , <a href="#">SW-18</a> , <a href="#">SW-19</a> , <a href="#">SW-21</a> , <a href="#">SW-22</a> , <a href="#">SW-23</a> , <a href="#">ST-1</a>			
Concrete Lined Channel			<a href="#">G-7</a> <a href="#">SD-1</a> <a href="#">SD-14</a> <a href="#">SD-15</a> <a href="#">SD-16</a>			
Cast-In-Place Sanitary Sewer Manholes		Section 4.8, Part 3.A.3	<a href="#">G-7</a> <a href="#">S-5</a> Note 15, <a href="#">S-13</a>	Air (if specified) , Slump, Compressive Strength		
Storm Sewer Manholes			<a href="#">G-7</a> <a href="#">SD-1</a> <a href="#">SD-10</a> <a href="#">SD-11</a> <a href="#">SD-12</a> <a href="#">SD-13</a>			
Inlets			<a href="#">G-7</a> <a href="#">SD-1</a> <a href="#">SD-2</a> <a href="#">SD-3</a> <a href="#">SD-4</a> <a href="#">SD-5</a> <a href="#">SD-6</a> <a href="#">SD-7</a>			
Concrete Medians		Section 5.1, Part 3	<a href="#">G-7</a> <a href="#">ST-5</a>	Slump, Compressive Strength		
Reinforced Concrete Headers			<a href="#">G-7</a>			
Concrete Steps			<a href="#">G-7</a>			
Retaining Walls (Structural)			<a href="#">G-7</a>	Air (if specified) , Slump, Compressive Strength	One set per placement	



## ENGINEERING DIVISION

**DISCLAIMER:** THE USE OF THIS STANDARD IS GOVERNED BY THE "TEXAS ENGINEERING PRACTICE ACT". NO WARRANTY OF ANY KIND IS MADE BY THE CITY OF WACO FOR ANY PURPOSE WHATSOEVER. THE CITY OF WACO ASSUMES NO RESPONSIBILITY FOR THE CONVERSION OF THIS STANDARD TO OTHER FORMATS OR FOR INCORRECT RESULTS OR DAMAGES RESULTING FROM ITS USE.

REVISIONS			
NO.	COMMENTS	BY	DATE
##	DESCRIPTION	FL	MM/DD/YYYY

DATE  
01/01/2024

G-1B